



STRIBECK ADDICHEM

PRODUCT DATASHEET
STRILUBE® 2131

SEMI-SYNTHETIC EMULSIFIER PACKAGE FOR MULTIMETALS

Strilube® 2131 is an advanced semi-synthetic emulsifier package crafted to deliver unparalleled performance across diverse multimetal applications. Designed for both moderate and heavy-duty machining and grinding, it strikes the perfect balance between efficiency and cost-effectiveness. Engineered to excel with cast iron, ferrous metals, alloys, aluminum, copper, and brass. Strilube® 2131 guarantees smooth, reliable, and high-precision operations. Elevate your industrial processes with this cutting-edge solution, setting a benchmark for superior performance and dependability.

Key features:

- Superior hard water stability for consistent performance in challenging water conditions
- Excellent multimetals corrosion inhibition.
- Excellent emulsification of base oils
- Good defoaming properties.
- Good tramp oil rejection.
- Improves surface finish & extends tool life.

Physio-chemical properties

Tests	Test Method	Results
Appearance	Visual	Clear liquid
Colour	Visual	Amber
Density at 29.5°C	ASTM D-1298	1 g/ml
Viscosity @40°C	ASTM D-445	195-250 cSt
Acid number	ASTMD-664	60-80 mg KOH/g

Applications:

Strilube®2131 is a high-quality solution for diverse selection of water-based metalworking fluids renowned for their superior corrosion inhibition properties.

Strilube® 2131 can be employed in various metal operations including grinding, milling, cutting, drilling, bending forming etc because of its excellent performance.

Some guidelines & their performance data with Strilube® 2131.

PARAFFINIC MID OIL 35% WITH STRILUBE 2131:

1	SN 150	35
2	STRILUBE 2131	35
3	DM WATER (FINISHED)	29.54
4	LAURYL ALCOHOL	0.2
5	BUTYL CARBITOL	0.2
6	FOAM BAN 970 (SFG)	0.06
	Total	100

Performance Data-

<i>PARAMETERS</i>	<i>RESULTS</i>
Appearance <i>Visual</i>	Clear Amber fluid
Stability at 0°C, 50°C & Room temp. <i>Visual</i>	Stable

Testing Parameters of 5% emulsion:

Appearance	Translucent
Hard water stability	Stable up to 1000 ppm
pH Value	9 to 10
Break Point % (IP287)	3%
RI Value	1.3
Foaming test (DM water)	15 secs.
Aluminium 5000 series corrosion test	Pass
Aluminium 6000 series corrosion test	Pass
Aluminium 7000 series corrosion test	Pass
Brass, Copper corrosion test	Pass

PARAFFINIC MID OIL 45% WITH STRILUBE 2131:

1	SN 150	45
2	STRILUBE 2131	35
3	DM WATER (FINISHED)	18.67
4	LAURYL ALCOHOL	1.3
5	FOAM BAN 970 (SFG)	0.03
	Total	100

Performance Data for above formulation:

<i>PARAMETERS</i>	<i>RESULTS</i>
Appearance <i>Visual</i>	Clear Amber fluid
Stability at 0°C, 50°C & Room temp. <i>Visual</i>	Stable

Testing Parameters of 5% emulsion:

Appearance	Milky White
Hard water stability	Stable up to 800 ppm
pH Value	9 to 10
Break Point % (IP287)	3%
RI Value	1.1
Foaming test (DM water)	20 secs.
Aluminium 5000 series corrosion test	Pass
Aluminium 6000 series corrosion test	Pass
Aluminium 7000 series corrosion test	Pass
Brass, Copper corrosion test	Pass

PARAFFINIC MID OIL 55% WITH STRILUBE 2131:

1	SN 150	55.00
2	STRILUBE 2131	35.00
3	DM WATER (FINISHED)	8.37
4	LAURYL ALCOHOL	1.6
5	FOAM BAN 970 (SFG)	0.03
	Total	100

Performance Data for above formulation:

<i>PARAMETERS</i>	<i>RESULTS</i>
Appearance <i>Visual</i>	Clear Amber fluid
Stability at 0°C, 50°C & Room temp. <i>Visual</i>	Stable

Testing Parameters of 5% emulsion:

Appearance	Milky-white
Hard water stability	Stable up to 800 ppm
pH Value	9 to 10
Break Point % (IP287)	3%
RI Value	1
Foaming test (DM water)	30 secs.
Aluminium 5000 series corrosion test	Pass
Aluminium 6000 series corrosion test	Pass
Aluminium 7000 series corrosion test	Pass
Brass,Copper corrosion test	Pass

Note: Performance data is summarized after several repetitive tests on the same formulation. Actual results may vary based on the test conditions and equipment used.

Packing: 200 Kg close head drum

Storage conditions: Store in a cool, dry place away from any direct source of heat and moisture. Maximum recommended storage temperature: 50°C

Solubility: Soluble in petroleum base stocks. Emulsifiable in water. However, it is recommended to verify the solubility in the base oils used and the compatibility with other additives.

Shelf life: Best if used within 12 months from the date of manufacture.

Manufactured by:

STRIBECK ADDICHEM

Email: lab@stribeckaddichem.com

Web: www.stribeckaddichem.com

Revision:03/03062025